




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21G 1/00, 1/02		A1	(11) International Publication Number: WO 98/44195
			(43) International Publication Date: 8 October 1998 (08.10.98)
(21) International Application Number: PCT/FI98/00269 (22) International Filing Date: 26 March 1998 (26.03.98) (30) Priority Data: 971342 2 April 1997 (02.04.97) FI (71) Applicant (for all designated States except US): VALMET CORPORATION [FI/FI]; Panuntie 6, FIN-00620 Helsinki (FI). (72) Inventor; and (75) Inventor/Applicant (for US only): VILJANMAA, Mika [FI/FI]; Otsolahdentie 18 A 6, FIN-02110 Espoo (FI). (74) Agent: FORSSÉN & SALOMAA OY; Yrjönkatu 30, FIN-00100 Helsinki (FI).		(81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.	

(54) Title: CALENDERING METHOD AND A CALENDAR THAT MAKES USE OF THE METHOD

(57) Abstract

The invention concerns a calendering method, in which the material web (W) to be calendered, in particular a paper or board web, is passed through the calender, in which at least one calendering nip (N) is formed by means of two rolls (12A, 12B) provided with resilient roll coatings (13A, 13B). The rolls (12A, 12B) are loaded towards each other so that, owing to the resilient nature of the roll coatings (13A, 13B), the nip (N) between the rolls (12A, 12B) becomes an extended nip. A flexible calendering belt (15A, 15B), which is non-compressible in comparison with the roll coatings (13A, 13B), which has been formed into an endless loop by means of alignment or reversing rolls (14A, 14B) or of equivalent rolls, and which runs through the nip, is passed over the calendering rolls (12A, 12B) provided with resilient roll coatings (13A, 13B) at each side of the nip (N). The invention also concerns a calender that makes use of the method.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Calendering method and a calender that makes use of the method

5

The invention concerns a calendering method, in which the material web to be calendered, in particular a paper or board web, is passed through the calender, in which at least one calendering nip is formed by means of two rolls provided with resilient roll coatings, which rolls are loaded towards each other so that, owing to the resilient nature of the roll coatings, the nip between the rolls becomes an extended nip.

The invention also concerns a calender that makes use of the calendering method, which calender comprises at least one calendering nip, which is formed by means of two rolls provided with resilient roll coatings, and through which calendering nip the material web to be calendered, in particular a paper or board web, has been passed, in which connection the rolls provided with resilient roll coatings are loaded towards each other so that, owing to the resilient nature of the roll coatings, the nip between the rolls becomes an extended nip.

20

When it is desirable to improve the standard of calendering, with the present solutions, in actual fact, the only possibility is to increase the number of calendering nips. This results in a more complicated construction of the calender and in more difficult control and tail threading of the paper web. Especially in the case of on-line machines, it must be possible to solve the contradictions arising from high running speed and from threading at full speed. Attempts have been made to solve these problems by means of various belt and shoe calenders, by whose means the calendering nip is extended and, thus, the operation of the nip is made more efficient. For example, in belt calenders, which in themselves are relatively recent constructions, the paper to be calendered is passed by means of an endless belt into a preliminary contact with a hot calender roll, in which case it is possible to create a steep temperature gradient, which is favourable from the point of view of calendering. By

30

means of the belt, the effective length of the nip is increased, owing to the preliminary contact and because, as the belt material, it is possible to use considerably softer polymers than in roll coatings without problems arising from deformations related to heat. With a nip longer than in a supercalender or soft calender, the press impulse applied to the paper can be increased so that the pressure peak does not become excessively high and that the bulk does not start decreasing.

One belt calender solution has been described in the prior art, for example, in the *Finnish Patent No. 95,061*. A calender embodiment in accordance with said publication is illustrated schematically in Fig. 1A in the drawing, which figure represents the prior art. Thus, Fig. 1A is a schematic illustration of a prior-art calender, in which the calendering nip N is formed between a heatable hard roll 1 and a calendering belt, in particular a metal belt 5, supported by a roll 2 with resilient coating. The metal belt 5 is an endless belt, and its material can be, for example, steel. The belt is passed over a nip roll 2 provided with a resilient coating 3 and over a reversing roll 4. As was already stated above, in this prior-art calender, the calendering nip N is, thus, formed between a heatable hard roll 1 and said metal belt 5, which is supported by a calender roll 2 provided with a resilient coating. Such a solution is, in fact, quite extensively similar to a nip in a soft calender, in which, however, by means of the metal belt 5, both faces of the paper W can be subjected to a substantially equal treatment and, thus, the glazing can be made to take place at both sides of the paper W at the same time.

Further, Fig. 1B illustrates a further development of the prior-art calender as shown in Fig. 1A. In the illustration in Fig. 1B, the calender has been extended to be a calender with two nips, so that the calender comprises two heatable hard-faced calender rolls 1A and 1B, two calender rolls 2A, 2B provided with resilient roll coatings 3A, 3B, and an endless metal belt 5. The endless metal belt 5 is passed over said rolls 2A, 2B with resilient coatings, and said rolls with resilient coatings form calendering nips N_1 , N_2 with the heatable hard-faced rolls 1A, 1B. More correctly, the calendering nips are formed, in each particular case, between the heatable hard-faced roll 1A, 1B and the metal belt 5, which metal belt 5 is loaded by

means of a corresponding roll 2A, 2B with a resilient coating against the heatable hard-faced roll 1A, 1B. As is shown in Fig. 1B, the paper web W is passed through the first nip N_1 , after which the web is spread and reversed by means of the take-out leading rolls 4A, 4B and guided into the second nip N_2 . The construction and the operation of the rolls 2A, 2B with resilient coatings are similar to the illustration in Fig. 1A. The prior-art calenders as shown in Figs. 1A and 1B are suitable for use with paper grades that do not require a long nip time to be glazed. Such paper grades are, for example, coated grades in which the glass transition temperature of the coating paste is low and in which, therefore, the glazing is rapid.

10

In view of on-line operation, a belt calender provides a significant advantage, among other things, in respect of the clear and linear running of the paper web, which again permits tail threading taking place at a high speed. In a belt calender supported by means of a glide shoe, the nip is formed between an endless belt and a steel roll. Owing to the glide shoe, the press zone becomes wider than in the belt calender described above. In a nip in a shoe calender, owing to the wider nip, the maximal pressure remains lower than in other present-day calenders, for which reason it is best suitable for paper grades in which retaining of the bulk has a high importance. As regards its construction, such a shoe calender is quite extensively similar to extended-nip presses, which have already been in use for a rather long time.

20

In respect of the prior art, as an example that represents shoe calendering, reference can be made, e.g., to the *Published German Patent Application No. 43 44 165*, wherein a smoothing method is described in which the fibrous web is passed in between two heatable faces which have been fitted at both sides of the web and which can be pressed against the web. The compression pressure can be regulated both in the running direction of the web and in the cross direction of the web in a way that has been chosen in advance. The prior art also includes the *US Patent No. 5,163,364*, which concerns a similar equipment provided with a glide shoe.

25
30

In respect of belt-supported calender concepts, reference is made additionally to the *US Patent No. 4,596,633*, in which a web finishing process is described, wherein the

surface portions of the web to be finished are first moistened to a high degree of moisture (dry solids content 50%...70%), and the web is then passed, on support of a belt, into a long finishing zone of low pressure, which zone comprises more than one roll nips. In said method, as the belt, prior-art paper machine fabrics are
5 employed, such as felts, wires or polymer belts, while the surface treatment proper is applied exclusively to the side of the web placed facing the backup roll.

In surface treatment devices provided with a glide shoe, it can be considered that the, at least partly dragging, contact between the belt and the glide shoe is a
10 problem, which contact applies quite a high strain both to the glide shoe and also to the belt. When a technology commonly employed in initial drying of a fibrous web has been applied, it has been realized that the quality of a belt that is well suitable for initial drying and that operates well in initial drying is inadequate in conditions of finishing of the web surface, in particular in respect of its resistance to the higher
15 strains applied to the belt. Also, of course, the high local strains applied to the belt in web break situations are an almost equally important problem as in polymer-coated rolls, even though a similar polymer present in belt form tolerates considerably higher strains than a coating attached to a roll face rigidly does. In shoe calenders with solutions provided with a glide shoe and a belt, it is a further problem
20 that the ends of the belt must always be closed, or spreading into the environment of the fluid and/or evaporation product employed in order to reduce the glide friction must be prevented in some other way.

A long belt circulation and a roll nip involve a similar basic problem. The quality of
25 the belt face and a homogeneous inner structure are an unconditional requirement in order that a uniform quality of web surface could be achieved, and, moreover, keeping the long belt loops, which are made of a more or less elastic material and which often comprise more than one belt alignment rolls, in their position in the cross direction of the web requires the construction of a regulation system of
30 remarkable complexity in connection with the finishing device.

5

The present invention concerns a calendering method and in particular a calendering method that makes use of a metal belt calender, in which, by means of endless metal belts, a calender with a very long nip is provided so that attempts are made to create all stages of the calendering process in one and the same calendering nip without
5 unnecessary additional operations. Thus, the object of the invention is to provide a calendering method that has been improved substantially, as compared with the prior art, and a calender that operates in accordance with this improved method, by means of which calender the calendering process can be made readily controllable and by means of which method the construction of the calender that carries out the method
10 can be made relatively simple. In view of achieving the objectives of the invention, the method in accordance with the invention is mainly characterized in that a flexible calendering belt, which is non-compressible in comparison with the roll coatings, which has been formed into an endless loop by means of alignment or reversing rolls or of equivalent rolls, and which runs through the nip, is passed over the calendering
15 rolls provided with resilient roll coatings at each side of the nip.

On the other hand, the calender in accordance with the invention is mainly characterized in that a flexible calendering belt, which is non-compressible in comparison with the roll coatings, which has been formed into an endless loop by means of
20 alignment or reversing rolls or of equivalent rolls, and which runs through the nip, has been passed over the calendering rolls provided with resilient roll coatings at each side of the nip.

By means of the invention, as compared with the prior-art calendering methods and
25 calenders, a number of significant advantages are achieved, of which, for example, the following can be stated in this connection.

When, in the present invention, a flexible, thin and substantially non-compressible belt is used in a novel way together with rolls provided with compressible or non-
30 compressible coatings, a very wide range of regulation of pressure is obtained together with a simultaneous range of high running speeds. Further, when a substantially non-compressible belt, whose material can be metal or, for example, a hard

polymer, such as a fibre-reinforced resin, and a roll that is provided with a resilient coating and that supports said belt at the nip are employed, a resilient finishing zone is obtained which has a face of very high quality and which is adapted against the web face very well in compliance with the loading. Further, by means of the solution in accordance with the invention, a finishing device is provided in which the overall length of the web treatment zone is very long and, if necessary, includes a number of zones with different pressure ranges. An essential feature of a calender in accordance with the present invention is the hardness of the calendering belt that is used, as compared with the roll coating. This provides the highly significant advantage that tail threading is free of problems and easy, for the leader end of the web can be passed through the calender as of full width without a risk that the web that is possibly wrinkled or clodded during the threading might cause permanent damage to the resilient coatings. The further advantages and characteristic features of the invention will come out from the following detailed description of the invention.

In the following, the invention will be described by way of example with reference to the figures in the accompanying drawing.

As was already stated above, Figs. 1A and 1B illustrate prior-art calenders so that Fig. 1A is a schematic illustration of a calendering nip which has been provided by means of a heatable hard roll and an endless metal belt that is supported by a roll provided with a resilient coating. On the other hand, Fig. 1B is a schematic illustration of a calender with two nips, in which the calendering nips are formed between hard rolls and a metal belt supported by rolls provided with resilient coatings.

Figure 2 is a schematic illustration of a calendering nip in accordance with the invention, which nip is formed between metal belts supported by means of rolls provided with resilient coatings at both sides of the nip.

BEST AVAILABLE COPY

Figure 3 illustrates a calender alternative to that shown in Fig. 2, in which calender the calendering nip is likewise formed between two metal belts supported by rolls provided with resilient coatings.

- 5 Figure 4 is a schematic illustration of a calender that has been developed further from Figs. 2 and 3 and by whose means a glazing in two stages can be carried out.

Regarding a calendering process in general, it can be stated that, in order that a paper could be made smooth and glazed from both sides, in the calendering nip there
10 must be a smooth face against each side of the paper. When an on-line calender is concerned, two opposite hard steel rolls form an excessively narrow nip in order that a deformation of the desired nature had time to arise in the paper at a high running speed. When each of the hard-faced calender rolls is substituted for by an endless calendering belt supported by a roll provided with a resilient coating, in particular
15 by a metal belt, a considerably extended nip is obtained, in which both sides of the paper are subjected to an equal treatment. The necessary pressing in the calendering nip is produced mainly by means of the rolls that support the calendering belts and partly by regulating the tension of the calendering belt. Depending on the requirement, the calendering belt can be supported either by hard rolls or by rolls provided
20 with resilient coatings. The effect of a calendering belt supported by hard steel rolls on the paper is similar to that in a machine calender, which means that variations in thickness of the paper are calibrated efficiently. However, since the nip time is considerably longer than in a machine calender, owing to the contact between the paper and the calendering belt and owing to the rigidity of the calendering belt, it
25 can be assumed that the desired visco-elastic deformation has time to take place to a greater extent than in an ordinary machine calender.

Steel belts supported against one another by means of rolls provided with resilient coatings subject the paper, at the rolls, to a press impulse similar to that in a
30 supercalender. Also, in the area between the rolls, the paper is subjected to a press impulse arising from the tension of the belts, the function of said impulse being mainly to prevent reversing of the deformations that arose at the rolls. When rolls

with resilient coatings are employed, the risk of damaging of the roll coatings is considerably lower than in a supercalender or soft calender, for the rolls are not in direct contact with the paper to be glazed, but the calendering belt protects the coatings efficiently from marking in the event of possible web breaks. The use of a calendering belt in a nip between the paper and a roll with resilient coating permits efficient cooling of the roll with resilient coating, which contributes to permitting a high running speed.

In the calendering process itself, the face of the paper to be calendered ought to be heated to a temperature higher than the glass transition temperature of the paper either before the calendering nip or, in an ideal case, in the nip itself. If the face of the paper has been heated in this way to the desired temperature, the face that presses the paper does not have to be hot any more, but the face can be preferably relatively cool, in which case, at the same time as the paper face in the soft state is pressed against the calendering face and becomes smooth, its temperature becomes lower, and the reversing of the deformation after the pressing is reduced. Such a solution, however, involves a certain contradiction, i.e. how to heat the face of the paper to such a high temperature so that the calendering faces in the calendering nip in contact with the paper face are not hot. Of course, the paper face can be heated in a cold nip if radiation energy is used for the heating and if the nip has been made of a material penetrable by said radiation.

Calendering can also be carried out as a so-called friction calendering, which is based, besides on the pressing of the paper placed between the faces, also on different speeds of the faces and the paper and on glide friction arising from said differences in speed. A normal copying arising from a press tension is intensified, besides owing to the rising of the temperature caused by the friction, also because the friction between the glazing face and the paper has been converted from static friction to kinetic friction, which is, as is well known, the lower one of these two. Even though, in the present-day solutions, gliding takes place in the machine direction only, the movement of the polymers is also facilitated in the cross direction because of the transition from the static friction to the kinetic friction. In the sol-

utions employed so far, the friction has been produced by rotating the rolls that form the nip at a slight mutual difference in speed. The extent of gliding per unit of length has been very little, but an improvement of the final result can, however, have been noticed. Problems are mainly runnability and precise regulation of the speeds of rotation of the rolls. Friction calendering can also be employed in an extended-nip calender that makes use of a calendering belt. In such a calender, even with a very little difference in speed between the faces, the gliding to which the paper is subjected is considerably large because of the extended nip. Such gliding can be produced, for example, by rotating the opposite calendering belts at slightly different speeds. In addition to the general principles of calendering described above, the invention will be illustrated in the following with reference to Figs. 1 to 3 in the drawing mentioned above with the aid of the particular alternative embodiments of the invention illustrated in said figures.

Fig. 2 is a fully schematic illustration of a calender, in which the calendering nip N has been formed between two calendering belts 15A, 15B supported by rolls provided with resilient coatings. The calendering belts 15A, 15B are preferably metal belts, in particular steel belts, but it is an essential feature of the invention that the belts are flexible and smooth belts non-compressible in comparison with the roll coatings 13A, 13B on the rolls 12A, 12B with resilient coatings. As was already stated above, the material of the belts is preferably steel, but it is also possible to contemplate that, as the material of the belt, for example, a fibre-reinforced, hard polymer belt or an equivalent belt material is used. Thus, each of the endless calendering belts 15A, 15B is passed over a roll 12A, 12B provided with a resilient roll coating 13A, 13B and over a reversing roll 14A, 14B. In respect of their construction and principle of operation, the rolls 12A, 12B with resilient coatings 13A, 13B, or at least one of them, can be, for example, a self-loaded roll 12A adjustable in zones, in which the roll mantle 16A is arranged to revolve around a stationary roll axle 17A, the roll mantle 16A being loaded in relation to said axle towards the nip N by means of loading elements 18A. By means of such a roll adjustable in zones, the load in the nip N can be made uniform in the cross direction of the web, and, if desired, the load can be regulated if necessary. If one of the rolls with resilient faces is, for

example, a roll 12A adjustable in zones, the roll 12B placed at the opposite side of the nip N does not necessarily have to be adjustable in zones in a similar way. In the case shown in Fig. 2, in view of achieving the desired calendering effect, the calendering belts 15A,15B must be heatable, because the rolls 12A,12B provided with resilient roll coatings 13A,13B cannot be made heatable in a corresponding way. The heating of the calendering belts 15A,15B can be carried out in a number of different ways, and as one of such ways, for example, induction heating can be mentioned. Induction heating can be employed if the belts are made of a metal material. In Fig. 2, the heating devices, in particular induction heaters, which heat the calendering belt 15A are illustrated fully schematically and denoted with the reference numeral 19A. Other modes of heating are, however, not excluded.

When the nip N has a width equal to that in a soft calender, at the same running speed and linear load, the paper web W is subjected to an equally high press impulse as in a soft calender. However, it is an advantage of the present invention, as compared with a soft calender, that at both sides of the paper there is a smooth hot metal face placed against the paper face, against which metal face the glazing can take place. Of course, in soft calenders, the primary function of the soft roll is just to make the nip longer and, thus, to increase the nip time. Glazing proper does not take place at the side of the soft roll almost at all, and therefore, in order to avoid unequalsidedness, in a soft calender at least two nips are needed, in which the roll positions are reversed in relation to one another.

It is one of the significant differences of the calender in accordance with the invention illustrated in Fig. 2, as compared with the solutions illustrated in Figs. 1A and 1B, which represent the prior art, that since the rolls 12A,12B placed at both sides of the nip N are rolls provided with resilient coatings 13A,13B, the geometry of the nip N becomes straight and the length of the nip N becomes longer than in the prior-art solutions shown in Figs. 1A and 1B, in which prior-art solutions the shape of the nip complies with the curve form of the steel roll. Thus, also in the case of Fig. 2, the nip time becomes substantially longer than in the solutions shown in Figs. 1A and 1B. From the point of view of the dimensioning of the calendering belt

15A,15B, a straight nip N provides an advantage, for in it the calendering belt 15A, 15B just becomes straight when it enters into the nip N, and the curve direction is not reversed, as it is reversed in the case of Figs. 1A and 1B. Thus, the improvement is significant in comparison with the prior art.

5

Fig. 3 shows a calender in which the calendering nip N through which the paper web W is passed is likewise formed between two calendering belts 15A,15B supported by rolls with resilient faces. Fig. 3, however, differs from the solution of Fig. 2 in the respect that the calendering belts 15A, 15B are guided by means of
10 alignment rolls 16A',16A" and 16B',16B", respectively, so that said calendering belts 15A,15B are in contact with the resilient roll coating 13A,13B in the nip N only. Such a solution is needed in particular if the formation of heat in the soft roll coatings 13A,13B causes problems. Also in the case of Fig. 3, the calendering belts 15A,15B have to be provided with purposeful heating devices in order to achieve the
15 desired temperature in the roll nip N. As the heating devices, it is possible to use, for example, induction heaters or equivalent. Since the roll coatings 13A,13B on the rolls 12A,12B that form the nip N are in contact with the hot calendering belt 15A,15B at the nip N only, the roll coatings 13A, 13B can be cooled efficiently almost over the entire length of the coating. The construction and the operation of
20 the rolls 12A,12B can be, for example, similar to those described in connection with the preceding embodiment of the invention. The embodiments shown in Figs. 2 and 3 are best suitable for use as calenders substituted for a soft calender.

Fig. 4 shows an embodiment of a calender in which there are two calendering nips
25 N_1 and N_2 placed one after the other. The first nip N_1 is formed between two hard rolls 11A,11B, such as steel rolls. Said hard rolls 11A,11B are preferably heatable rolls. The second nip N_2 is formed between two rolls 12A,12B provided with resilient roll coatings 13A,13B, however, so that endless calendering belts 15A,15B have been passed over the hard rolls 11A,11B and over the resilient-face rolls
30 12A,12B placed at each side of the nips. Thus, the paper W runs between the nips N_1 and N_2 in a closed space between the calendering belts 15A,15B. As compared with the prior art, this solution provides a significant advantage in particular in the

respect that, in normal cases, after a hot nip, the paper is in the most troublesome state, in which connection a quick releasing of the pressure may spoil the whole paper. Now the pressure cannot be released quickly after the first nip, but, as was already described above, the paper runs between the calendering belts 15A,15B on their support from the first nip N_1 into the second nip N_2 .

When hard rolls, in particular heatable hard rolls are used as the pair of rolls 11A, 11B in the first nip N_1 , in the nip N_1 it is possible to use a very high calendering pressure, in which case the effect is equal to a machine calender. At a high calendering pressure, the paper tends to be widened in the lateral direction, which again tends to produce cross-direction gliding between the paper and the calendering belt 15A,15B. Cross-direction gliding improves the calendering of the paper W if the calendering belts 15A,15B support the paper so much that folding of the paper is prevented. Such folding produces micro-tears in the paper web. The pair of rolls in the second nip N_2 consists of rolls 12A,12B with resilient faces. Their function is, within a press zone wider than in the pair of rolls 11A, 11B and with a lower linear load, to finish the calendering result by applying a glazing effect similar to soft-calendering to both faces of the paper.

~~20~~ In the case of the first pair of rolls 11A,11B, the calendering is almost exclusively based on compression of the paper. Between the nips N_1 and N_2 , shear forces between the paper faces and the calendering belts 15A,15B and the heat conducted from the calendering belts to the paper face are effective. In the portion of the paper web that has reached the area of the latter pair of rolls 12A,12B, a temperature gradient has had time to be formed, so that the faces of the paper have been heated beyond the glass transition temperature of the polymers contained in the faces, and the primary calendering mechanism is copying of the face of the smooth calendering belt to the face of the paper. The formation of the temperature gradient can be regulated by varying the nip length and by thereby acting upon the time of dwell and by regulating the temperature of the calendering belts. Between the nips N_1 and N_2 , inside the calendering belts 15A,15B, actuators 19 may have been fitted, by whose

means the calendering belts are either cooled or heated or high-frequency oscillation is produced in the calendering belts 15A, 15B.

In consideration of the calendering process, it can be stated further that, in particular
5 in the case of a metal belt, the calendering belt can be heated. In the case of other materials, and also in the case of a metal material, the calendering belt can be, for example, cooled, moistened, etc., as required. Such a solution is very well suitable for one-sided calendering, in particular for calendering of board. In the calender, one belt can be heated and the belt placed at the opposite side of the nip can be
10 cooled, in which case a phenomenon is produced in which the moisture present in the material web to be calendered can be made to be transferred in the calendering nip from the heated side to the cooled side. Earlier, it was already stated that one essential feature of the belt is its hardness in comparison with the roll coating. This provides the highly significant advantage that the threading is free from problems
15 and easy, for the end of the web can be passed through the calender as of full width.

Above, the invention has been described just by way of example with reference to the figures in the accompanying drawing. The invention is, however, not confined to the exemplifying embodiments shown in the figures alone, but different embodi-
-20 —ments of the invention may show variation within the scope of the inventive idea defined in the accompanying patent claims.

Claims

1. A calendering method, in which the material web (W) to be calendered, in particular a paper or board web, is passed through the calender, in which at least one calendering nip (N) is formed by means of two rolls (12A,12B) provided with resilient roll coatings (13A,13B), which rolls are loaded towards each other so that, owing to the resilient nature of the roll coatings (13A,13B), the nip (N) between the rolls (12A,12B) becomes an extended nip, characterized in that a flexible calendering belt (15A,15B), which is non-compressible in comparison with the roll coatings (13A,13B), which has been formed into an endless loop by means of alignment or reversing rolls (14A,14B;16A',16A",15B',16B") or of equivalent rolls (11A,11B), and which runs through the nip, is passed over the calendering rolls (12A,12B) provided with resilient roll coatings (13A,13B) at each side of the nip (N).
2. A calendering method as claimed in claim 1, characterized in that, in order to produce the necessary calendering temperature and to plasticize the surface layer of the material web (W) to be calendered, at least one of the calendering belts (15A, 15B) is heated.
- ~~3. A calendering method as claimed in claim 1 or 2, characterized in that, in order to calender the material web (W) from both sides in the same calendering nip (N,N₂), both calendering belts (15A,15B) are heated.~~
4. A calendering method as claimed in any of the preceding claims, characterized in that, in particular in a case in which the calendering belts (15A,15B) are metal belts, the heating of said calendering belts is carried out by means of induction heating (19;19A).
5. A calendering method as claimed in claim 1 or 2, characterized in that the calendering belt that is placed at the opposite side of the nip (N) in relation to the calendering belt to be heated is cooled.

BEST AVAILABLE COPY

6. A calendering method as claimed in any of the preceding claims, **characterized** in that the length of the calendering nip (N) is regulated by regulating the position of at least one alignment or reversing roll (14A;16A',16A"/14B;16B',16B") of a calendering belt (15A/15B) running at least at one side of the nip.

5

7. A calendering method as claimed in claim 1, **characterized** in that the calendering belts (15A,15B) passed over the calendering rolls (12A,12B) provided with resilient roll coatings (13A,13B) are passed over hard rolls (11A,11B), which form a nip (N₁) with each other so that the web (W) to be calendered is supported by
10 means of calendering belts (15A,15B) between the belts substantially over the entire distance between the nip (N₁) formed by the hard rolls (11A,11B) and the nip (N₂) formed by the calendering rolls (12A,12B) provided with resilient roll coatings (13A,13B).

15 8. A calendering method as claimed in claim 7, **characterized** in that the hard rolls (11A,11B) or at least one of said hard rolls is/are heated in order to produce the desired calendering temperature.

9. A calendering method as claimed in claim 7 or 8, **characterized** in that the
20 ~~calendering belts (15A,15B) are cooled between the calendering nips (N₁,N₂).~~

10. A calendering method as claimed in claim 7 or 8, **characterized** in that the calendering belts (15A,15B) are heated between the calendering nips (N₁,N₂).

25 11. A calendering method as claimed in any of the claims 7 to 10, **characterized** in that high-frequency oscillation is produced in the calendering belts (15A,15B) between the calendering nips (N₁,N₂).

30 12. A calender that makes use of a calendering method as claimed in any of the preceding claims, which calender comprises at least one calendering nip (N), which is formed by means of two rolls (12A,12B) provided with resilient roll coatings (13A,13B), and through which calendering nip (N) the material web (W) to be

calendered, in particular a paper or board web, has been passed, in which connection the rolls (12A,12B) provided with resilient roll coatings (13A,13B) are loaded towards each other so that, owing to the resilient nature of the roll coatings (13A, 13B), the nip (N) between the rolls (12A,12B) becomes an extended nip, character-
5 ized in that a flexible calendering belt (15A,15B), which is non-compressible in comparison with the roll coatings (13A,13B), which has been formed into an endless loop by means of alignment or reversing rolls (14A,14B;16A',16A'',15B',16B'') or of equivalent rolls (11A,11B), and which runs through the nip, has been passed over the calendering rolls (12A,12B) provided with resilient roll coatings (13A,13B) at
10 each side of the nip (N).

13. A calender as claimed in claim 12, characterized in that, in order to produce the necessary calendering temperature and to plasticize the surface layer of the material web (W) to be calendered, at least one of the calendering belts (15A,15B)
15 is arranged to be heatable.

14. A calender as claimed in claim 12 or 13, characterized in that, in order to calender the material web (W) from both sides in the same calendering nip (N,N₂), each calendering belt (15A,15B) has been arranged to be heatable.

20 15. A calender as claimed in any of the claims 12 to 14, characterized in that, in particular in a case in which the calendering belts (15A,15B) are metal belts, said calendering belts are provided with induction heaters (19;19A).

25 16. A calender as claimed in claim 12 or 13, characterized in that the calendering belt that is placed at the opposite side of the nip (N) in relation to the calendering belt to be heated is provided with cooling means.

30 17. A calender as claimed in any of the claims 12 to 16, characterized in that the length of the calendering nip (N) is arranged to be regulated by regulating the position of at least one alignment or reversing roll (14A;16A',16A''/14B;16B',16B'') of a calendering belt (15A/15B) running at least at one side of the nip.

18. A calender as claimed in claim 12, characterized in that the calendering belts (15A,15B) passed over the calendering rolls (12A,12B) provided with resilient roll coatings (13A,13B) are passed over hard rolls (11A,11B), which form a nip (N_1) with each other so that the web (W) to be calendered is supported by means of
5 calendering belts (15A,15B) between the belts substantially over the entire distance between the nip (N_1) formed by the hard rolls (11A,11B) and the nip (N_2) formed by the calendering rolls (12A,12B) provided with resilient roll coatings (13A,13B).


19. A calender as claimed in claim 18, characterized in that the hard rolls (11A,
10 11B) or at least one of said hard rolls is/are a heatable roll/rolls in order to produce the desired calendering temperature.

20. A calender as claimed in claim 18 or 19, characterized in that the calendering belts (15A,15B) are provided with cooling devices in the area between the calender-
15 ing nips (N_1, N_2).

21. A calender as claimed in claim 18 or 19, characterized in that the calendering belts (15A,15B) are provided with heating devices in the area between the calender-
ing nips (N_1, N_2).

20

22. A calender as claimed in any of the claims 18 to 21, characterized in that the calendering belts (15A,15B) are provided with devices which are fitted to produce a high-frequency oscillation in said belts between the calendering nips (N_1, N_2).



PRIOR ART




FIG. 1B




FIG. 2




FIG. 3




FIG. 4

INTERNATIONAL SEARCH REPORT

International Application No

PCT/FI 98/00269

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 D21G1/00 D21G1/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D21G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 698 684 A (VALMET PAPER MACHINERY INC) 28 February 1996 see column 5, line 1 - column 5, line 15; figure 5 ---	1
A	US 4 998 333 A (SKYTAE OSMO) 12 March 1991 see the whole document ---	1
A	PATENT ABSTRACTS OF JAPAN vol. 096, no. 012, 26 December 1996 -& JP 08 209582 A (NIPPON PAPER IND CO LTD), 13 August 1996, see abstract ---	1
A	US 5 137 678 A (HESS HARALD ET AL) 11 August 1992 see the whole document ---	1
-/--		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "Z" document member of the same patent family

Date of the actual completion of the international search

13 July 1998

Date of mailing of the international search report

23/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Guisan, T

INTERNATIONAL SEARCH REPORT

Int. .onal Application No

PCT/FI 98/00269

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 3 804 707 A (MOHR W ET AL) 16 April 1974</p> <p>see the whole document</p> <p>-----</p>	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/FI 98/00269

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0698684 A	28-02-1996	FI 943620 A	05-02-1996
US 4998333 A	12-03-1991	FI 80098 B	29-12-1989
		DE 3920742 A	04-01-1990
		SE 467163 B	01-06-1992
		SE 8902325 A	30-12-1989
US 5137678 A	11-08-1992	DE 4011394 C	28-11-1991
		AT 111542 T	15-09-1994
		CA 2039956 A,C	10-10-1991
		DE 59102892 D	20-10-1994
		EP 0451449 A	16-10-1991
		FI 911668 A,B,	10-10-1991
US 3804707 A	16-04-1974	NONE	